



**Founded, Based and  
MADE IN THE U.S.A.**

Rapid Setting Cement Based  
Hydraulic Cement

### DESCRIPTION:

AQUA PLUG's instant setting can be achieved in 2-3 minutes to stop pressure leaks in concrete and masonry surfaces. This rapid set allows AQUA PLUG to bond mechanically and chemically to saturate surfaces.

### USES AND APPLICATIONS:

- Stops Streaming Leaks in Concrete
- Anchors Bolts and Rods
- Seals Cracks and Floor and Wall Junctions

### PRODUCT FEATURES:

- Non-Metallic, Non Rusting
- Fast Setting
- Stops water leaks under pressure
- Easy to mix
- Single component
- Expands as it sets
- Waterproof
- Chloride and metal free mortar
- Freeze-Thaw stable
- Can be shaved and molded to desired contour
- Once set, AQUA PLUG is resistant to hydrostatic pressure

### SUBSTRATE PREPARATION:

Slightly undercut the hole to be plugged and enlarge small cracks to permit embedment of material. Recommended minimum size of hole or crack is 0.75 in. wide and deep. Remove all loose dirt or aggregate. Surfaces should be SSD (Saturated Surface Dry) prior to placement.

### MIXING:

Mix AQUA PLUG with clean potable water. Add just enough to make a putty consistency. Water ratio is 3 parts powder to 1 part water. AQUA PLUG is to be mixed in small quantities only due to rapid set time.

### APPLICATION:

Apply AQUA PLUG with trowel or by hand to seeping area starting at top of crack. Hold firmly in place exerting pressure with hand or trowel for about 3 minutes to be sure AQUA PLUG does not wash out under water pressure. If small leaks should appear around the patched area, sprinkle AQUA PLUG in a dry form onto the leaking area, or mix a small batch of AQUA PLUG to a soft putty consistency and hold firmly over area till set.

**STOP STREAMING WATER:** Begin at top of crack and place AQUA PLUG in firmly using some force to place into opening. Continue to apply pressure with trowel or by hand until material sets and active water has stopped.

**SEALING CRACKS, FLOOR /WALL JUNCTIONS:** Firmly push AQUA PLUG into crack or hole to form a cove at the floor and wall junction.

**ANCHORING BOLTS OR RODS:** Drill or chisel a hole deep enough to hold bolt or rod securely and at least 1/2" space on all sides of bolt or rod. Position the bolt in the hole, use a small pointed trowel and fill in AQUA PLUG completely around bolt. Smooth off surface with trowel while supporting bolt with hand for about one minute until it does not sag.

**03 61 00**  
Cement Grouting

**3**

**03 50 00**  
Concrete Repair

**3**

### **PACKAGING:**

50 lb. Pail

### **COLOR:**

Light Grey

### **SHELF LIFE:**

12 months

### **REQUIRED TOOLS:**

Safety Gloves  
Mixing Bucket  
Trowel

### **MIXING RATIO:**

3 Parts Powder to 1 Part Water

### **WEIGHT / CUBIC FOOT:**

130 ft.<sup>3</sup> Installed

### **APPROXIMATE COVERAGE:**

50 lb. Unit Yields: 0.50 ft.<sup>3</sup>

2 1/2 pounds will fill a crack 3/4" wide by 3/4" deep and 75" in length

### **APPLICATION TEMPERATURE**

#### **RANGE:**

35° - 95°F

### **SET TIME:**

2-3 Minutes

### **COMPRESSIVE STRENGTH (ASTM C 109)**

4 Hours	2000 psi	13.8 MPa
1 Day	4000 psi	31.0 MPa
28 Days	5500 psi	37.9 MPa

# AQUA PLUG

## APPLICATION NOTES:

1. It is the responsibility of the contractor to review the complete technical datasheets of CMP products referenced above as more detailed information may be required. The information provided above acts only as a general guideline and may vary based on jobsite conditions.
2. Apply AQUA PLUG immediately after mixing.
3. Do not mix more than can be placed within 2 minutes.
4. Not for use in moving cracks.
5. Not for use as a surface applied material or coating.
6. Wet substrate prior to placement keeping the material wet for a minimum of 15 minutes.

**Eligible LEED credits : 5**  
Recycled Content (MR 4.1 & 4.2)  
2 Points

Regional Materials (MR 5.1 & 5.2)  
2 Points

Low Emitting Materials (EQ 4.1)  
1 Point

### **STORAGE:**

Store in cool dry place. Tightly seal package and do not expose to sun.

### **FLAMMABILITY: (ASTM E-84)**

Flame Spread: -0-

Fuel Contribution: -0-

Smoke Development: -0-

### **VOLATILE ORGANIC COMPOUNDS**

0 g/l

### **CLEAN UP:**

Clean tools with water immediately after use or by mechanical means once dry.

### **HEALTH AND SAFETY:**

Always refer to the Safety Data Sheet (SDS) prior to using this product for full Health, Safety and Handling guidelines. SDS sheets are available by calling 267.522.8000 or you can visit [www.cmpsp.com](http://www.cmpsp.com)

For Professional Use Only

**KEEP OUT OF REACH OF CHILDREN**

