## ESTES' CERAMAQUARTZ Ceramic Coated Aggregate Product Data Sheet

Estes Ceramaquartz aggregates are ceramic coated and designed for use in swimming pool finishes and epoxy seamless flooring applications.

## Typical Particle Size Analysis and Properties (This does not represent a specification)

S-Grade		
USA Standard Sieve Size	Individual % Retained	
16	0	
20	0	
30	15.4	
40	45.2	
50	23.2	
70	11.7	
100	3.7	
140	0.7	
200	0.1	

American Foundrymen's Society Grain Fineness	10
Mohs Hardness	7
Shape	Angular
Mineral	Quartz

<u>T-Grade</u>	
USA Standard Sieve Size	Individual % Retained
8	0
12	<1
16	48
20	51
30	1
50	0

Chemical Resistance Data		
<u>Acid</u>	Concentration (%)	
Nitric Acid	70	
Hydrochloric Acid	37	
Acetic Acid	100	
Sulfuric Acid	96	
Chromic Acid	82	
Muriatic Acid		
Chlorine	1 part to 2 parts water	
Alkaline	Concentration (%)	
Trisodium Phosphate	40	
Sodium Carbonate	20	
Ammonium Hydroxide	28	
Industrial Detergent	1 part to 2 parts water	

<u>Disclaimer:</u> The information set forth in the Product Data Sheet represents typical properties of the product described; the information and the typical values are not specifications. Clifford W. Estes Co. Inc. makes no representation or warranty concerning the products, expressed or implied, by this Product Data Sheet.

Clifford W. Estes Co., Inc. 40 Vreeland Ave Ste 104 Totowa, NC 07512 (800) 248-2271