



Sales Office:
Engineered Synthetic Products, Inc.
Tel (770) 564-1857
Fax (770) 564-1818
www.espgeosynthetics.com

Geotextile Product Description Sheet

SKAPS GT-140 Nonwoven Geotextile

SKAPS GT-140 is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. SKAPS GT-140 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. SKAPS GT-140 conforms to the physical property values listed below:

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Weight (Typical)	ASTM D 5261	oz/yd ² (g/m ²)	4.0 (136)
Grab Tensile	ASTM D 4632	lbs (kN)	100 (0.445)
Grab Elongation	ASTM D 4632	%	50
Trapezoid Tear Strength	ASTM D 4533	lbs (kN)	50 (0.222)
CBR Puncture Resistance	ASTM D 6241	Lbs (kN)	300 (1.32)
Permittivity*	ASTM D 4491	sec ⁻¹	2.0
Water Flow*	ASTM D 4491	gpm/ft ² (l/min/m ²)	140 (5689)
AOS*	ASTM D 4751	US Sieve (mm)	70 (0.212)
UV Resistance	ASTM D 4355	%/hrs	70/500

PACKAGING	
Roll Dimensions (W x L) – ft	12.5/15 x 360
Square Yards Per Roll	500/600
Estimated Roll Weight - lbs	146/172

* At the time of manufacturing. Handling may change these properties.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.

SKAPS Industries,
335 Athena Drive, Athens GA 30601
Phone:(706)-354-3700, Fax(706)-354-3737,
www.skaps.com

Made in U.S.A.