AQ™ COPING / WALL DETAIL



PRODUCT INFO :

Depth - 12”
Length - 24”
Nose height - 2 3/4”
Heel height - 1 1/4”
Max finish wall - 11”

Available in Color - Yes
Available in tile openings - Yes
Available in radius options - Yes

All measurements are for consideration purposes only. Nominal measurements, please contact us for a sample slice.

Federal Stone Coping : Precast concrete, formed using various types of sand, aggregates, integral pigmentations if required, and portland cements.

ASTM STANDARD

- Air enviroments : ASTM C231
  - 4% by voulme
- Compressive strengths : ASTM C172
  - 24 hours - 3800 psi
  - 7 Days - 6000 psi
  - 28 days - 7500 psi
- Freeze thaw : ASTM C457
  - Current test run excess of 300 cycles
- Moisture absorption : ASTM C192
  - 24 hours - 3.1% average
- Static coefficient of friction : ASTM C1028 / ADA 4.5.1
  - Standard surface - Dry 0.75 excellent / Wet 0.60 suitable
  - Terrazzo surface - Dry 0.80 excellent / Wet 0.70 excellent