

MicroTop 5000

Gray/White Hybrid Micro Topping

630-GW

USE:

ICT MicroTop 5000 is used to enhance new or existing, Concrete surfaces with a customized smooth decorative finish. Can be used along with *ICT Color Seal H2O Pro*, *ICT Water Shades System*,

SURFACE PREPARATION:

To successfully install *ICT MicroTop 5000*, the surface must be dry, clean, free of all algae, grease, oil, dirt and all other foreign matter (*ICT Total Klean*, all purpose cleanser & degreaser, is recommended). Removal of algae & mildew may be achieved with a solution of bleach (diluted 1-3 parts water). On previously painted or coated surfaces, sand blasting will be required to remove any prior coating. New concrete surfaces should be allowed to cure a minimum of 7-10 days prior to installing *MicroTop 5000*. It is recommended that all surfaces be pressure washed prior to application of *MicroTop 5000*, allowing to dry thoroughly prior to installation (24 hrs.).

MIXING INSTRUCTIONS:

MIX MICROTOP 5000 WITH APPROXIMATELY 4-5 QTS OF COOL POTABLE WATER. MIX TO A PANCAKE BATTER CONSISTANCY. APPLY WITH A TROWEL OR SQUEEGEE. ALLOW TO DRY COMPLETELY BEFORE SEALING WITH COLORSEAL OR CLEAR SEAL. DO NOT APPLY WHEN SURFACE TEMPS ARE BELOW 52 DEGREES FEHRENHEIT.

CHARACTERISTICS AND TECHNICAL DATA

Package...	50 lb. bag
Color (dry)....	Gray/White
Consistency when mixed....	"pancake batter"
Pot Life when mixed @ 70°F	30-45 min.
Spray coverage per bag...	250 sq. ft.at 1/16"
Installation <u>Surface</u> Temp...	min. 52°F
Dry to touch @ 70°F...	1-2 hrs.
Dry to Color Seal...	min. 4-8 hrs.
Dry for light traffic...	min. 24 hrs.
Dry for heavy traffic...	min. 48-72 hrs.

Thickness of material, low temperature & high humidity will significantly lengthen drying time.

High temperatures will shorten pot life of mixed material.

ICT Corporation

2410 McJunkin Road * Lakeland, FL 33803

(Nationwide): 888-296-5236 * (Local): 863-665-8787 *(Fax): 863-666-2768

(Email): info@innovativeconcrete.com

www.innovativeconcrete.com

All Innovative Concrete Technology Corp. products are manufactured with the finest raw materials. Shelf life is 1 year from the date of manufacturing when maintained in protected storage of 50°F to 90°F. It is the applicator's responsibility to determine the appropriate use of the product. All recommendations and suggestions are made without warranty, express or implied, since conditions of use are beyond ICT control. ICT Corp. disclaims any liability incurred in connection with the use of these data or suggestions.