



FASTSET CONCRETE MIX

A rapid hardening concrete mix designed with a 20-30 minute set time, allowing for mixing, pouring and finishing. Use at any thickness from 1-1/2" to 24".

Use to build or repair:

- Street repairs
- Concrete parking lots
- Highways
- Concrete floors
- Bridge decks
- Sidewalks

Compressive Strength ASTM C 39

3 Hours	3000 psi	20.7 MPa
24 Hours	5000 psi	34.5 MPa
7 Days	6000 psi	41.3 MPa
28 Days	7000 psi	48.3 MPa

Exceeds the requirements of ASTM C 928 R-3

Item No.	Package Size	Metric	Quantity
1004-51	70 lb. bag	31.7 kg	42/pallet



FASTSET REPAIR MORTAR

A low-sag repair mortar formula. Ideal for vertical & overhead repairs. 20-30 minute working time & unique properties allow sculpting of the material during placement.

Use for repairing:

- Pre-stress panels
- Retaining walls
- Tunnels
- Loading docks
- Bridge columns
- Curbs/steps

Compressive Strength ASTM C 109 Modified

3 Hours	2000 psi	13.8 MPa
24 Hours	4000 psi	27.6 MPa
7 Days	5000 psi	34.5 MPa
28 Days	6000 psi	41.4 MPa

Exceeds the requirements of ASTM C 928 R-2

Item No.	Package Size	Metric	Quantity
1241-20	20 lb. pail	9.1 kg	60/pallet
1241-50	50 lb. pail	22.7 kg	each
1241-60	60 lb. bag	27.2 kg	56/pallet



FASTSET NON-SHRINK GROUT

For structural concrete repairs from 1/4" to 24" deep. 30 minute set time, non shrink characteristics & rapid strength gain. Can be mixed to a plastic, flowable or fluid consistency.

Use for anchoring & grouting:

- Anchor bolts
- Steel column bases
- Bearing plates
- Floor leveling
- Pre-cast concrete keyways

Compressive Strength ASTM C 109

Time	Fluid	Flowable	Plastic
3 Hours	2000 psi (13.8 MPa)	2500 psi (17.2 MPa)	3000 psi (20.7 MPa)
24 Hours	4000 psi (27.6 MPa)	4500 psi (31.0 MPa)	5000 psi (34.5 MPa)
7 Days	5000 psi (34.5 MPa)	5500 psi (37.9 MPa)	6000 psi (41.3 MPa)
28 Days	6500 psi (44.8 MPa)	7500 psi (51.7 MPa)	8000 psi (55.1 MPa)

Exceeds the requirements of ASTM C 928 R-3 and ASTM C 1107.

Item No.	Package Size	Metric	Quantity
1585-20	20 lb. pail	9.1 kg	60/pallet
1585-50	50 lb. pail	22.7 kg	each
1585-09	60 lb. bag	27.2 kg	56/pallet



NON-SHRINK PRECISION GROUT

High strength, non-metallic, non-shrink grout designed for precision grouting and general construction applications. Can be mixed to a plastic, flowable or fluid consistency.

Use For:

- Grouting heavy equipment, pre-cast concrete, bearing plates, steel columns and anchoring applications

Compressive Strength at 28 Days

Plastic	14,000 psi	96.5 MPa
Flowable	12,000 psi	86.2 MPa
Fluid	8,000 psi	55.2 MPa

Meets the requirements of ASTM C 1107 and Army Corp. of Engineers CRD 621

Item No.	Package Size	Metric	Quantity
1585-00	50 lb. bag	22.7 kg	64/pallet
1585-00	50 lb. bag	22.7 kg	35/mini pallet

January 2003 Introduces current QUIKRETE® logo & new packaging

May 2003 Runs national TV ad featuring Concrete Resurfacer

January 2006 Introduces Veneer Stone Mortar & FastSet DOT Mix

