



Type A Chlorinated Rubber Pool Paint

TECHNICAL BULLETIN 11-13

- For upgrading and restoring previously painted chlorinated rubber surfaces
- Self-priming, gloss finish
- Up to 5 years service life
- Excellent coverage rate



Used in the industry for decades to restore and protect plaster and concrete pool surfaces. Excellent choice for recoating previously painted chlorinated rubber surfaces. It is formulated to provide excellent hiding and superior coverage rates compared to other chlorinated rubber paints.

PHYSICAL DATA	APPLICATION DATA
VEHICLE TYPE: Chlorinated Rubber	METHOD: Brush, Use no thicker than 3/8" Mohair or Lambskin Roller, Airless or Conventional Spray.
FINISH: Gloss	NUMBER OF COATS: 2 (Product is self – priming)
COLORS: AquaGreen, White, Black, Dawn Blue Monument Gray, Dark Blue, Royal Blue, French Gray.	DRY FILM THICKNESS PER COAT: 1.0 mils (2.9 mils wet)
COMPONENTS: 1	APPLICATION TEMP: 50° F. Min. / 90°F. Max.
CURING MECHANISM: Air Dry	DRY TIME* (Days): 5-7 days—Outdoor pool to refill pool
SOLIDS (theoretical):	10-14 w/adequate ventilation— Indoor pool to refill pool
By weight...54%+/- 1%	To Recoat: 24 Hours
By volume...35+/- 1%	
COVERAGE: 200—300 sq. ft. on bare surface	
350—400 sq. ft. on recoats	
VOC: 600 g/l max. (as supplied)	THINNER:
FLASH POINT: 84°F (SETA)	Ramuc Thinner

www.ramucpoolpaint.com - (800) 745-6756