



# AquaLuster Acrylic Pool Paint

TECHNICAL BULLETIN 11-13

- For preciously painted acrylic based coatings.
- Self-priming, high gloss finish
- Cleans up with soap and water
- Up to 2 years service life



Ramuc AquaLuster is formulated to offer tremendous advantages while complying with strict environmental and state VOC regulations. This acrylic water-based coating is best used in top-coating previously painted acrylic painted surfaces.

PHYSICAL DATA	APPLICATION DATA
VEHICLE TYPE: Acrylic Latex	METHOD: Brush, Use no thicker than 3/8" Mohair or Lambskin Roller, Airless or Conventional Spray.
FINISH: Gloss	NUMBER OF COATS: 2 Product is self – priming
COLORS:	DRY FILM THICKNESS PER COAT: 1.5 mils (4.5 wet mils)
Brilliant White, Black, Dawn Blue, AquaGreen,	APPLICATION TEMP: 50° F. Min. / 90°F. Max.
Dark Blue, Brick Red, Royal Blue, Monument	DRY TIME* (Days): 5 days Outdoor pool
Gray	To Recoat: 6 Hours
COMPONENTS: 1	Before Filling: 5 days outdoor pool
CURING MECHANISM: Air Dry	RESTRICTIONS: Not for bare concrete surfaces, epoxy finishes or spas.
SOLIDS (theoretical):	
By weight...46.0% +/- 2% (White & Pastel colors)	
By volume...33.0 +/- 1% (White & Pastel colors)	
COVERAGE: 400—450 sq ft/	
VOC: 250 g/l max. (as supplied)	
FLASH POINT: > 200° F (SETA)	