



Pro 2000 Chlorinated Rubber Pool Paint

TECHNICAL BULLETIN 11-13

- Commercial chlorinated rubber pool paint.
- For previously painted chlorinated rubber surfaces.
- Self-priming, flat finish
- Up to 2 years service life



Ramuc Pro 2000 Chlorinated Rubber Pool Paint has been designed for commercial use where a competitively priced paint is required and pool maintenance is performed every few years. Excellent choice for recoating previously painted chlorinated rubber surfaces.

PHYSICAL DATA	APPLICATION DATA
VEHICLE TYPE: Chlorinated Rubber	METHOD: Brush, Use no thicker than 3/8"
FINISH: Flat	Mohair or Lambskin Roller, Airless or
COLORS: AquaGreen, White, Black, Dawn Blue	Conventional Spray.
COMPONENTS: 1	NUMBER OF COATS: 2 (Product is self –
CURING MECHANISM: Air Dry	priming)
SOLIDS (theoretical):	DRY FILM THICKNESS PER COAT: 1.0 mils
By weight...57%+/- 2%	(3.0 mils wet)
By volume...35+/- 1%	APPLICATION TEMP: 50° F. Min. / 90°F. Max.
COVERAGE: 150-175 sq. ft. on bare surface	DRY TIME* 5-7 days Outdoor before filling pool
250-300sq ft/ on recoats	To Recoat: 24 Hours
VOC: 575 g/l max. (as supplied)	THINNER:
FLASH POINT: 84°F (SETA)	Ramuc Thinner
	Xylene