

SOUTHERN PRODUCTS & SILICA COMPANY



NSF/ANSI/CAN 61

Incorporated 1933

Filter Sand & Gravel - Industrial Sand - Well Gravel Packs - Quartz Gravel - Epoxy Aggregate

Plant located at 4303 U.S. Highway 1 North, Hoffman, NC 28347

www.sandandgravel.net

P.O. Drawer 189 Hoffman, NC 28326

Fax: 910-281-3815 Sales Orders Fax: 910-281-3213 Administration

Phone: 910-281-3189 Toll Free: 800-572-6348

General Information / Technical Data

Our materials are hard quartzite, sub-angular sand and rounded gravel, free of clay, silt, iron, mica and other foreign matter. All filtering material is washed, screen-sized, washed and sized again according to current American Water Works Association B100 Standards for Filtering Materials and are NSF listed.

Water Filter Sand and Gravel

Filter Sand

Effective Size (ES)	Uniformity Coefficient (UC)
.45mm55mm	U.C. 1.6 or less
.80mm-1.20mm	U.C. 1.6 or less
2.0mm-3.0mm	U.C. 1.6 or less

Custom Filter Sand ES and UC Available Upon Request

Filter Gravel

	A MILLER GIATO
2 1/2 x 1 1/2	1/2 x 1/4
1 1/2 x 1	3/8 x 3/16
1 1/2 x 3/4	1/4 x 1/8
1 x 5/8	3/16 x #10
1 x 1/2	#5 x #16
3/4 x 1/2	1/8 x #16
5/8 x 3/8	

Industrial Sand

<u>Grade</u>	Approximate Sieve Size
Ultra Fine	30-140
Extra Fine	25-80
Fine	10-45
Medium	8-30
Coarse	4-20

Quartz Gravel for Catalyst Support

1 1/2 x 3/4 / 1 1/4 x 3/4 / I x 1/2

Epoxy Aggregates

Available in various sizes.

Chemical Analysis Example (% By Weight)

Calcium (Ca)	< 0.01%
Calcium Oxide (CaO)	<0.01%
Calcium Carbonate (CaCO ₃)	<0.01%
Magnesium (Mg)	0.05%
Magnesium Oxide (MgO)	0.09%
Magnesium Carbonate (MgCO ₃)	0.19%
Iron Oxide (Fe ₂ O ₃)	0.03%
Aluminum Oxide (Al ₂ O ₃)	0.17%
Silicon (Si)	46.56%
Silicon Dioxide (SiO ₂)	99.61%
Sulfur Trioxide (SO ₃)	0.04%
Manganese (Mn)	<0.01%
Loss on Ignition	0.14%

Well Gravel Packs

Product	Approximate Sieve Size
Gravel Pack #1	16-50
Gravel Pack #1A	10-40
Gravel Pack #2	7-35
Gravel Pack #3	5-20
Gravel Pack #4	4-12

Geothermal Sand

Our Geothermal Sand has been used extensively throughout the Industry

Ask about special sizing and gradation requirements.



SOUTHERN PRODUCTS & SILICA COMPANY



Incorporated 1933

Filter Sand & Gravel - Industrial Sand - Well Gravel Packs - Quartz Gravel - Epoxy Aggregates

Assurance of Quality

Full service laboratory testing continually monitors sand & gravel specifications for compliance with standards. All filtering materials meet current AWWA B100 standards and are NSF listed. Certified testing analysis is available on all filter sand and gravel shipments.

Transportation

All material can be shipped by truck, bagged or bulk.

Packaging

Products are bagged in .5 cu. ft. or 1.0 cu. ft. clear plastic bags (LDPE), or woven 3000 lb. super sacks. Dry palletized bags are shrink-wrapped and have a top cover sheet that provides both rain and UV protection. All material is quoted with pallet. Pallets are Non-Stackable 40"x40", 40"x44", or 40"x48". Heat Treated Option For Export. You can also order our material bulk, delivered via dump bed or pneumatic tanker.

Pricing

Prices for all materials depend on selected packaging options.

Prices are quoted F.O.B. Hoffman, NC

Ordering Information

Our sales staff will be pleased to assist you between the hours of 8 A.M. and 4:00 P.M., Monday - Friday. Please Call or Email:

POST OFFICE DRAWER 189 4303 U.S. HIGHWAY 1 NORTH HOFFMAN, NC 28347

TOLL FREE: 800-572-6348

PHONE: 910-281-3189

FAX: 910-281-3815 SALES ORDERS

FAX: 910-281-3213 ADMINISTRATIVE

