

# PERMEABLE PAVERS

DRIVEWAYS, PERMEABLE DRIVEWAYS & PATIOS








## PHYSICAL AND GEOMETRICAL CHARACTERISTICS - PAVERS

CHARACTERISTICS	CSA A231.2	TECHO-BLOC
Compressive strength	50 MPa [7200 psi] min.	50 MPa [7200 psi] min.
Absorption	-	5 % max.
Freeze-thaw durability with use of de-icing salt	Mass loss (max.): 225 g/m <sup>2</sup> at 28 cycles 500 g/m <sup>2</sup> at 49 cycles	Mass loss (max.): 225 g/m <sup>2</sup> at 28 cycles 500 g/m <sup>2</sup> at 49 cycles
Dimensional tolerance	Length and Width: -1.0 mm [0.039 in.] to +2.0 mm [0.079 in.] Thickness: ±3.0 mm [0.118 in.]	Length and Width: -1.0 mm [0.039 in.] to +2.0 mm [0.079 in.] Thickness: ±3.0 mm [0.118 in.]

Notes : Dimensional tolerances prior to the application of architectural finishes.

# Installation guide

## TYPICAL APPLICATION USAGE

SECTOR	TRAFFIC TYPE & APPLICATIONS	PERMEABLE PAVERS
RESIDENTIAL	 <p><b>1. Light traffic</b> Cars and occasional light service trucks (ex. residential driveways)</p>	<ul style="list-style-type: none"> <li>- Antika</li> <li>- Blu 80 mm</li> <li>- Inflo</li> <li>- Mista Random</li> <li>- Pure</li> <li>- Valet</li> <li>- Victorien 60 mm permeable</li> <li>- Villagio</li> </ul>
	 <p><b>2. Pedestrian</b> Pedestrian only and at all times (ex. patios)</p>	<ul style="list-style-type: none"> <li>- Antika</li> <li>- Blu 80 mm</li> <li>- Blu 60 mm</li> <li>- Inflo</li> <li>- Mista Random</li> <li>- Pure</li> <li>- Valet</li> <li>- Victorien 60 mm permeable</li> <li>- Villagio</li> </ul>
ICI (Industrial, Commercial and Institutional)	 <p><b>3. Road traffic</b> Cars, heavy trucks, buses (ex. boulevards, main or secondary streets, pedestrian crossings, industrial, ports and airport areas)</p>	<ul style="list-style-type: none"> <li>- Inflo</li> </ul>
	 <p><b>4. Light traffic</b> Cars and occasional light service trucks (ex. parking lots, sidewalks)</p>	<ul style="list-style-type: none"> <li>- Inflo</li> <li>- Pure</li> </ul>
	 <p><b>5. Pedestrian</b> Pedestrian only and at all times, without cars, or trucks or other mobile equipment (ex. terraces, parks, pedestrian walkways)</p>	<ul style="list-style-type: none"> <li>- Inflo</li> <li>- Pure</li> </ul>

# Installation guide


## INFILTRATION CHART

PERMEABLE PAVERS	PERCENT OF SURFACE OPENING (%)	JOINT WIDTH (mm)	INFILTRATION RATE <sup>1</sup> (mm/h)
ANTIKA <sup>2</sup>	Variable	Variable	993 in./hr (25 227 mm/hr)
BLU 80 mm <sup>2</sup>	3.0	9/32" (7 mm)	570 in./hr (14 475 mm/hr)
INFLO <sup>1</sup>	5.8	1/2" (13 mm)	837 in./hr (21 267 mm/hr)
MISTA RANDOM <sup>1</sup>	6.3	3/16" (4 mm) to 9/16" (14 mm)	610 in./hr (15 505 mm/hr)
PURE <sup>2</sup>	5.0	3/8" (10 mm)	726 in./hr (18 440 mm/hr)
VALET	5.9	9/32" (7 mm)	to come
VICTORIEN 60 mm PERMEABLE <sup>1</sup>	9.6	3/8" (10 mm)	909 in./hr (23 085 mm/hr)
VILLAGIO <sup>1</sup>	8.0	3/8" (9 mm) to 9/16" (15 mm)	896 in./hr (22 750 mm/hr)
PERMEABLE SLAB	PERCENT OF SURFACE OPENING (%)	JOINT WIDTH (mm)	INFILTRATION RATE <sup>1</sup> (mm/h)
BLU 60 mm <sup>2</sup>	3.0	9/32" (7 mm)	570 in./hr (14 475 mm/hr)

<sup>1</sup>Measurements were taken at various sites in conformity to the standard ASTM C 1701-09.

<sup>2</sup>Measurements were taken at various sites in conformity to the standard ASTM C 1781.

### OTHER PERMEABLE POSSIBILITIES



Blu 60 mm  
SLAB

(page 28 to 33)




Antika  
PAVER

(page 53)




Blu 80 mm  
PAVER

(page 54 to 58)



Mista Random  
PAVER

(page 72)



Valet  
PAVER

(page 81)



Villagio  
PAVER

(page 83)

# Installation guide

## SEGMENTAL PERMEABLE PAVEMENT



### INSTALLATION OUTLINE

#### 01 DATA COLLECTION

- A. Determine the size, shape, and intended use of finished areas (i.e. residential driveway, secondary commercial parking, etc.).
- B. Classify sub-grade soils.
- C. Document all existing conditions (i.e. fixed points, existing grades, site contours, etc.).
- D. Document soil type, location, and elevation of below grade and overhead utilities both public and private.
- E. Ensure public utilities are marked through the use of a locating service.
- F. Determine the cross section design of the system based on soil type and application, showing proposed sub-grade and finished grade elevations and all geotextiles and drainage pipes needed for the construction.
- G. Establish the type, location, and elevation of relief structures if required (i.e. overflow pipe discharging to rain garden, etc.).
- H. Determine the curb or edge restraint type, elevation, and location.
- I. Choose a pattern appropriate to the application (traffic type and load).

#### 02 EXCAVATION

- A. Before digging, contact the concerned companies if wires or pipes are located in the area to be excavated.
- B. Excavation depth is determined from the foundation thickness according to the project specifications (foundation thickness is determined by a qualified engineer based on structural and hydrological analyses).
- C. Although the slope of the sub-grade will depend on the drainage design and infiltration type, a minimum slope of 0.5% ( $\frac{1}{16}$ " per ft, or 5 mm per meter) is recommended.
- D. The distance that the excavated area should extend beyond the area to be paved should be one to 1.5 times the thickness of the foundation. This extra space will ensure the stability of the pavers near the edge and the edge restraints.
- E. Level the bottom of the excavated area with a rake.

Compaction will reduce the permeability of the sub-grade and it should be executed according to the project specifications. If compaction is not specified, care should be taken to maintain undisturbed soil infiltration during excavation and construction. Stabilization of the sub-grade may be required with weak, continually saturated soils, or when subject to high traffic conditions. If the compaction or stabilization of sub-grade is necessary, reduced infiltration may require drainage pipes within the sub-base to conform to storm water drainage requirements.

#### 03 GEOTEXTILE, IMPERMEABLE LINERS, AND DRAIN PIPES

- A. Use the geotextile specified and install it according to project specifications. The use of a woven geotextile with bi-axel strength that meets design criteria is recommended.
- B. Place the geotextile on the bottom and sides of the soil sub-grade. Eliminate wrinkles in the geotextile and ensure it is not damaged during construction.
- C. Overlap of geotextile should be a minimum of 2' (600 mm) in the direction of drainage. Overlapping should be "shingle" style with respect to any slope direction and base stone distribution direction. Keep properly tensioned, eliminate wrinkles, and avoid damaging fabric (no spikes).
- D. If impermeable liners are required, install them according to project specifications and manufacturer's instructions. Impermeable liners are used when full exfiltration from the reservoir (sub-base and base) into the underlying sub grade is not allowed (no infiltration design). Perforated drainage pipes are usually required in no infiltration and partial infiltration designs.
- E. If drainage pipes are required, install them according to project specifications. The aggregate cover over drainage pipes should be at least 12" (300 mm) to protect them from damage during sub-base or base compaction.

# Installation guide

## SEGMENTAL PERMEABLE PAVEMENT

### 04 SUB-BASE

For residential pedestrian applications, the sub-base may not be required and then only ASTM No. 57 (CSA 5-28) aggregate base layer with a minimum thickness of 6" (150 mm) can be used (use a thicker base for additional water storage). Refer to Base (see below 06).

When traffic load, soil conditions, and climate require greater than 12" (300 mm) of base or volume requirements for detention are higher, a sub-base may be required. Use sub-base ASTM No. 2 or No. 3 (CSA 40-80) meeting the following requirements:

- 90% fractured symmetrical particles
  - Less than 5% passing the 200 sieve
  - Industry hardness tested
- A. Moisten, spread and compact the ASTM No. 2 (CSA 40-80) aggregate sub-base in minimum 6" (150 mm) lifts (without distorting or damaging the geotextile) according to the project specifications.
  - B. Make at least two passes in the vibratory mode followed by at least two passes in the static mode with a minimum 10 ton (9 metric ton) vibratory roller, until there is no visible movement of the aggregate. Alternately, a 13,500 lbf (60 kN) plate compactor can be used to compact the ASTM No. 2 (CSA 40-80) aggregate sub-base.
  - C. Do not allow the compactor to crush the aggregate.
  - D. Surface tolerance of the ASTM No. 2 (CSA 40-80) sub-base should be ffl 2 1/2" (64 mm) over 10' (3 m).

### 05 EDGE RESTRAINT

- A. Install edge restraint according to project specifications.
- B. Depending on the design, the top of the edge restraint can be hidden or exposed.
- C. Install Avignon, Belgik, Pietra, Tundra or Universal edge units. Cast-in-place concrete or precast concrete curbs should be considered in vehicular use applications (commercial / industrial driveways, parking lots or streets).
- D. Edge restraint may rest on an open-graded or dense-graded aggregate base.

### 06 BASE

- A. Moisten, spread and compact the ASTM No. 57 (CSA 5-28) aggregate base layer in one 4" (100 mm) thick lift.
- B. Make a minimum of two passes in vibratory mode followed by at least two in static mode with a minimum 10 ton (9 metric ton) vibratory roller, until there is no visible movement of the aggregate. Alternately, a 13,500 lbf (60 kN) plate compactor can be used to compact the ASTM No. 57 (CSA 5-28) aggregate base.
- C. Do not allow the compactor to crush the aggregate.
- D. Surface tolerance of the ASTM No. 57 (CSA 5-28) base should be ffl 1" (25 mm) over 10' (3 m). Verify prior to setting bed installation.

### 07 BEDDING COURSE

- A. Moisten, spread and screed the ASTM No. 8 (CSA 2.5-10) aggregate bedding layer in one 2" (50 mm) thick lift.
- B. Surface tolerance of the ASTM No. 8 (CSA 2.5-10) bedding course should be ffl 3/8" (10 mm) over 10' (3 m).
- C. Construction equipment and pedestrian traffic on the screeded bedding course should not be permitted.

### 08 PAVER

- A. Pavers should be placed in the pattern shown on the drawings. Lay units hand tight to designated laying patterns. Units have lugs to maintain consistent joint width.
- B. In sloped conditions, it is preferable to start laying from the bottom in an uphill direction.
- C. The minimum slope recommended for permeable pavement surface is 1%.
- D. Inflow pavers can be installed with the TB100SI (Techo-Bloc mechanical tool) to expedite installation.
- E. When subject to vehicular traffic, cut units should not be smaller than 1/3 of a whole paver. When using cut pieces, maintain joint.
- F. In vehicular applications, pattern strength will increase if laying pattern is perpendicular to traffic flow.

# Installation guide

## SEGMENTAL PERMEABLE PAVEMENT

### 09 JOINT FILL

- A. Fill the paver joint openings with ASTM No. 8 (CSA 2.5-10) aggregate (or No. 89, No. 9 depending on joint width). Sweep stone to fill joints. Surface must be swept clean prior to compaction.
- B. Compact with a minimum 5,000 lbf (22 kN) plate compactor (two passes minimum). The installation of a neoprene pad is recommended to protect the texture of the paving units.
- C. Do not compact within 6' (1.8 m) of unrestrained edges of the pavers.
- D. Apply additional aggregate to fill the joint openings if needed and compact.
- E. Surface tolerance of compacted pavers should be ffl  $\frac{3}{8}$ " (10 mm) over 10' (3 m).

### APPROXIMATE MEASURES

Clean stone quantity in kg (lb) to cover an area of 1 m<sup>2</sup> (1 pi<sup>2</sup>) to fill between joints.  
*It is recommended to always start with a small area.*


PRODUCTS	JOINT FILL MATERIAL	(lbs/sq. ft)	(kg/sq. m)
Antika	ASTM No. 8 (CSA 2.5 - 10) ( $\frac{1}{4}$ "	1.9	9.3
Blu 60 mm	ASTM No. 9 (CSA 2.5 - 5) ( $\frac{1}{8}$ "	0.6	3.0
Blu 80 mm	ASTM No. 9 (CSA 2.5 - 5) ( $\frac{1}{8}$ "	0.8	4.0
Inflo	ASTM No. 8 (CSA 2.5 - 10) ( $\frac{1}{4}$ "	2.1	10.3
Mista random	ASTM No. 9 (CSA 2.5 - 5) ( $\frac{1}{8}$ "	1.0	5.0
Pure	ASTM No. 9 (CSA 2.5 - 5) ( $\frac{1}{8}$ "	1.4	7.0
Valet	ASTM No. 9 (CSA 2.5 - 5) ( $\frac{1}{8}$ "	1.3	6.2
Victorien 60 mm permeable	ASTM No. 9 (CSA 2.5 - 5) ( $\frac{1}{8}$ "	1.7	8.5
Villagio	ASTM No. 8 (CSA 2.5 - 10) ( $\frac{1}{4}$ "	2.1	10.2

### 10 POST INSTALLATION PROTECTION

Prevent contamination of the porous (permeable) pavement system from fine aggregates and debris by maintaining erosion and sedimentation (E&S) measures at the perimeter.

# Installation guide


## SEGMENTAL PERMEABLE PAVEMENT



- A. PERMEABLE PAVER FROM TECO-BLOC
- B. JOINT FILLING MATERIAL  
ASTM No 8 (CSA 2.5-10 mm) AGGREGATE
- C. BEDDING COURSE 1½" to 2" (40 to 50 mm)  
ASTM No 8 (CSA 2.5-10 mm) AGGREGATE
- D. BASE COURSE 4" (100 mm)  
ASTM No 57 (CSA 5-28 mm) AGGREGATE
- E. SUBBASE COURSE  
ASTM No 2 (CSA 40-80 mm) AGGREGATE
- F. GEOTEXTILE
- G. SUBGRADE
- H. CONCRETE EDGE

### SEGMENTAL PERMEABLE PAVEMENT – FULL INFILTRATION


Typical cross section



- A. PERMEABLE PAVER FROM TECO-BLOC
- B. JOINT FILLING MATERIAL  
ASTM No 8 (CSA 2.5-10 mm) AGGREGATE
- C. BEDDING COURSE 1½" to 2" (40 to 50 mm)  
ASTM No 8 (CSA 2.5-10 mm) AGGREGATE
- D. BASE COURSE 4" (100 mm)  
ASTM No 57 (CSA 5-28 mm) AGGREGATE
- E. SUBBASE COURSE  
ASTM No 2 (CSA 40-80 mm) AGGREGATE
- F. GEOTEXTILE
- G. SUBGRADE
- H. CONCRETE EDGE
- I. PERFORATED DRAIN CONNECTED TO  
DRAINAGE SYSTEM

### SEGMENTAL PERMEABLE PAVEMENT – PARTIAL INFILTRATION

Typical cross section



- A. PERMEABLE PAVER FROM TECO-BLOC
- B. JOINT FILLING MATERIAL  
ASTM No 8 (CSA 2.5-10 mm) AGGREGATE
- C. BEDDING COURSE 1½" to 2" (40 to 50 mm)  
ASTM No 8 (CSA 2.5-10 mm) AGGREGATE
- D. BASE COURSE 4" (100 mm)  
ASTM No 57 (CSA 5-28 mm) AGGREGATE
- E. SUBBASE COURSE  
ASTM No 2 (CSA 40-80 mm) AGGREGATE
- F. IMPERMEABLE MEMBRANE
- G. SUBGRADE
- H. CONCRETE EDGE
- I. PERFORATED DRAIN CONNECTED TO  
DRAINAGE SYSTEM

### SEGMENTAL PERMEABLE PAVEMENT – NO INFILTRATION

Typical cross section